

AD-A086 710

DEFENCE RESEARCH ESTABLISHMENT ATLANTIC DARTMOUTH (NO--ETC F/G 7/4
QUANTITATIVE ELECTRON PROBE MICROANALYSIS USING A SCANNING ELEC--ETC(U)
APR 80 D E VEINOT
DREA-TM-80/A


UNCLASSIFIED

NL

1-1
710-1



END
DATE
FILMED
8-80
DTIC



LEVEL II

3
B.S.

UNLIMITED
DISTRIBUTION
ILLIMITEE

DEFENCE RESEARCH ESTABLISHMENT
ATLANTIC


ADA086710

QUANTITATIVE ELECTRON PROBE MICROANALYSIS
USING A SCANNING ELECTRON MICROSCOPE
AND AN X-RAY ENERGY SPECTROMETER

DTIC
ELECTE
S JUL 10 1980

A

✓ D.R.E.A. TECHNICAL MEMORANDUM 80/A



RESEARCH AND DEVELOPMENT BRANCH
DEPARTMENT OF NATIONAL DEFENCE
CANADA

80 7 8 079

DEFENCE RESEARCH ESTABLISHMENT ATLANTIC

9 GROVE STREET

P.O. BOX 1012
DARTMOUTH, N.S.
B2Y 3Z7

TELEPHONE
(902) 426-3100

CENTRE DE RECHERCHES POUR LA DÉFENSE ATLANTIQUE

9 GROVE STREET

C.P. 1012
DARTMOUTH, N.E.
B2Y 3Z7

**RESEARCH AND DEVELOPMENT BRANCH
DEPARTMENT OF NATIONAL DEFENCE
CANADA**

DEFENCE RESEARCH ESTABLISHMENT
ATLANTIC

DARTMOUTH N.S.

(9) D.R.E.A. TECHNICAL MEMORANDUM 80/A

(14) DREA-TM-80/A

(6) QUANTITATIVE ELECTRON PROBE MICROANALYSIS
USING A SCANNING ELECTRON MICROSCOPE
AND AN X-RAY ENERGY SPECTROMETER.

(10) Dwight E. Veinot
(11) April 1980

Approved by J. R. BROWN

A/Director / Technology Division

(12) 22

DISTRIBUTION APPROVED BY

Jac. Ferguson

CHIEF D.R.E.A.

RESEARCH AND DEVELOPMENT BRANCH
DEPARTMENT OF NATIONAL DEFENCE
CANADA

403761 *Ja.*

+ 26 -

ABSTRACT

A procedure was developed to utilize a scanning electron microscope and X-ray energy spectrometer to obtain quantitative elemental analysis. The precision and accuracy of an X-ray intensity ratio data processing technique has been evaluated. In general, the quantitative results obtained were accurate to better than ± 1 percent of the certified elemental compositions of standard reference materials for all elements present at greater than 2 weight percent. Results were reproducible to better than 1 percent of the determined percentage compositions. Elements present at less than 0.1 weight percent composition and elements having atomic numbers less than 11 (sodium) were not detected.

Accession For	
NTAS General	<input checked="" type="checkbox"/>
DDC Lab	<input type="checkbox"/>
Unprocessed	<input type="checkbox"/>
Just Received	<input type="checkbox"/>
By _____	
Distribution _____	
Availability _____	
List	Availability for special
A	

SOMMAIRE

On a mis au point un procédé qui utilise un microscope électronique à balayage et un spectromètre d'énergie de rayons-X afin de procéder à l'analyse quantitative des éléments. On a procédé à l'évaluation de la précision ainsi que de la fiabilité d'une technique de traitement numérique des rapports d'intensité des rayons-X. De façon générale, les résultats quantitatifs obtenus avaient une précision supérieure à ± 1 pourcent des compositions bien connues en éléments présents dans des matières de référence étalons pour le cas de tous les éléments présents dans une proportion supérieure à 2 pourcent en poids. Les résultats pouvaient être reproduits dans une proportion qui dépassait 1 pourcent des compositions déterminées en pourcentage. Les éléments dont la présence représentait moins de 0.1 pourcent en poids de la composition et les éléments dont les numéros atomiques étaient inférieurs à 11 (sodium) n'ont pas été décelés.

TABLE OF CONTENTS

	<u>Page No.</u>
ABSTRACT	11
NOTATION	v
1. INTRODUCTION	1
2. EQUIPMENT	1
3. EXPERIMENTAL PROCEDURE	2
3.1 Approach	2
3.2 System Calibration	2
3.3 Sample Preparation	3
3.4 Electron Beam Parameters	3
3.5 Data Acquisition	4
4. RESULTS AND DISCUSSION	5
5. SUMMARY	6
ACKNOWLEDGEMENT	7
TABLES	8
ILLUSTRATIONS	11
REFERENCES	12
DOCUMENT CONTROL DATA	15

NOTATION

SEM	scanning electron microscope
XES	X-ray energy spectrometer
FWHM	full width half maximum
eV	electron volt
KV	kilovolt
ac	alternating current
Å	Angstrom
mm	millimeter
μm	micrometer
cps	counts per second
ADC	analog to digital converter
PGT	Princeton Gamma Tech
NBS	National Bureau of Standards
SRM	Standard Reference Material

1. INTRODUCTION

The use of X-rays to obtain chemical analysis has expanded since the relationship between X-ray line frequency and atomic number was first discovered¹. One of the most recent advances in this area was the development of solid state, energy dispersive radiation detectors. Such devices can be fitted conveniently to scanning electron microscopes and can accurately resolve the energies of X-rays produced by electron bombardment of the sample (target) material in the SEM.

The high energy resolution capability of lithium drifted silicon radiation detectors has resulted in considerable interest in their potential use as analytical devices². The most interesting feature of these devices is their capability to rapidly and simultaneously detect and discriminate X-ray energies. Energy dispersive spectrometers have been used in combination with electron microprobes and electron microscopes to simultaneously obtain chemical and topographical information on samples such as metals, plastic, glass, rubber, solvent residues, ceramics, semi-conductors, paints, airborne particulates and corrosion products. Several reports^{3,4,5,6,7,8,9} have been published describing the analytical applications of electron probe microanalysis. Some of these^{4,5,7,9} contain information concerning accuracy, precision and detection limits obtained using energy dispersive spectrometers for chemical analysis.

The aim of this work was to develop and evaluate a procedure to utilize a SEM-XES combination to obtain rapid and reliable chemical analyses during a microscopic examination. This procedure enables an analyst to obtain chemical information from very small samples (less than 1 μm^2) and also to isolate and analyze specific areas of interest on the surfaces of larger samples.

2. EQUIPMENT

An Advanced Metals Research (AMR) model 1000A SEM which incorporates a pre-aligned electron optical column, a secondary electron detector and a specimen stage assembly which enables specimen rotation, tilt and x, y, and z translation was used for this work. The display console contains

a cathode ray tube display screen together with electron optics controls such as magnification, working distance, brightness, contrast, accelerating voltage, filament current and beam alignment.

A Princeton Gamma Tech (PGT) lithium "drifted" silicon X-ray detector model 1S-15 complete with associated PGT model PO-12 preamplifier, model 340 main amplifier, model 343 live time corrector and a 7.5 litre liquid nitrogen dewar formed the basis of the X-ray detector system. The detector bias voltage (-1000V dc) was provided by a Tennelec model TC 947 supply. The detector resolution was 148 eV FWHM at 5.9 keV and 1000 cps.

A Tracor Northern NS 880 X-ray analysis system consisting of a magnetic cassette tape transport, an NS 623 analog to digital converter (ADC) having 8192 channels and a PDP 11/05 computer with 20 K of core memory was used to acquire and process the X-ray data. Software used with this system was developed by Tracor Northern.

An Edwards model 306 vacuum coater was used to deposit a thin conducting carbon film on the surfaces of specimens in order to reduce charge build-up caused by electron bombardment inside the SEM.

A Keithley model 602 electrometer was used in conjunction with a device prepared in the laboratory to measure electron beam currents.

An Invertron model LC-1201B dynamic AC line corrector provided a stabilized voltage from 110V ac mains.

3. EXPERIMENTAL PROCEDURES

3.1 Approach

An X-ray intensity ratio technique formed the basis for the quantitative analytical procedure which was developed. Elemental X-ray intensities from the sample being analyzed were compared to the corresponding pure element X-ray intensities. Selected standard reference materials (NBS) were used to evaluate the accuracy and precision of the technique.

3.2 System Calibration

The front end electronics of the X-ray analysis system were calibrated using X-rays released from a pure moly-

bdenum specimen. The molybdenum L α X-ray (2293 eV) and K α X-ray (17478 eV) provided a convenient means of adjusting energy calibration over a wide energy range (15185 eV).

3.3 Sample Preparation

All samples were mounted in epoxy resin and polished to a flat smooth surface using standard metallographic techniques. The polished specimens were cleaned in methanol to remove excess polishing compound and dried in air. A thin (100 Å) conductive carbon layer was deposited on the specimen surfaces in order to prevent charge build-up on the non-conducting epoxy mounts during the analyses.

A graphite rod (spectrographic grade) was machined to 1 mm diameter (EFFA Sharpener, Ernest F. Fullam, Inc., N.Y.) and set to provide a 5 mm burn in the Edwards vacuum coater in order to reproduce carbon coatings of the same thickness. Carbon was used for the coating material because it is conductive, does not appreciably affect the electron beam bombardment or X-ray emission and does not itself produce X-rays which are detected by the system.

3.4 Electron Beam Parameters

The rate of production of X-rays from the sample surface is directly proportional to the rate of electron bombardment upon the specimen surface (beam current). Therefore, in order to obtain a material balance in chemical analyses it was necessary to measure and control beam current during the acquisition of pure element reference spectra and during subsequent analyses of samples of unknown composition using these references. A means of measuring beam current at the sample surface was not available for the AMR model 1000A SEM so a device (Figure 1) was prepared in the laboratory and fitted to the SEM stage assembly as follows. A 1 mm i.d., 4 mm deep cylindrical hole was drilled into a solid piece of aluminum. This hole was covered with a metallic foil having a 500 μ m i.d. aperture to allow electron beam entrance to the drilled cavity. Electrically conducting silver paint (Number 1481 silver paint E.F. Fullam, N.Y.) was used to assemble this device and secure it to a standard aluminum specimen stub so that it could be conveniently fitted to the specimen stage assembly. The stage assembly was connected to an electrical contact leading to the outside of the electron optical column using insulated copper wire. A Keithley model 602 electrometer was connected to this outside contact using a short length (20 cm) of shielded coaxial cable.

The carbon coated specimens (pure element standards and NBS certified standard reference materials) and the alu-

minum cage were positioned on the stage assembly using a multiple sample holder similar to that described by Green¹⁰. The use of this holder enables the analysis of several samples without requiring separate introduction of these samples into the sample chamber. This is particularly useful when using the SEM-XES combination to analyze several samples because it allows each specimen to be analyzed without having to re-establish electron beam or column conditions between the analyses.

The electron beam was focused onto the specimen surface. The Z-translational adjustment was used to provide a working distance* of 12 mm which was held constant for each analysis. The tilt adjustment was used to provide a take-off angle** of 35 degrees from each sample surface. The electron beam was then focused into the hole in the aluminum cage. The resulting current was measured with the Keithley electrometer. Typical currents produced were of the order of 10^{-9} amperes. A current of 0.5×10^{-9} amperes was selected for the quantitative procedure because it was easily obtained and remained steady for long periods of time (hours). The beam current was adjusted and controlled as required using the filament current and beam alignment controls on the SEM. Current measurements were made before and after each analysis. Typically these measurements did not vary by more than ± 4 percent.

3.5 Data Acquisition and Processing

Using an accelerating voltage of 30 kV, the X-ray energy spectrum of each of the pure element standards was obtained and stored on magnetic tape. The X-ray energy spectrum of each of the NBS certified standard reference materials used to evaluate the technique was obtained in a similar manner.

X-ray intensity ratios (k_i) were converted to elemental concentration ratios (c_i) using the Tracor Northern Super ML¹¹ and ZAF¹² computer programmes which were designed to process the basic expression:

$$c_i = k_i(ZAF)_i$$

* Distance from column anode to sample surface.

** Angle formed by the sample surface and the path of X-rays to the detector at the point of electron beam penetration.

where Z is an atomic number penetration correction factor and A and F are computed absorption and fluorescence correction factors for element i . Since each of the three correction terms requires a knowledge of the concentrations for all elements in the sample, it is necessary to solve the ZAF corrections in an iterative manner similar to that used by J. Colby in the Magic IV programme¹³. In that programme the estimated concentrations are set equal to the input k ratios and the concentrations are then normalized to sum to 100 percent. Using the normalized c_i values, the ZAF factors for each element are computed from expressions developed by Duncumb and Reed¹⁴.

4. RESULTS AND DISCUSSION

Tables 1, 2, and 3 show the results obtained for the analyses of three different alloys. Table 1 shows the results obtained for NBS SRM 162a monel alloy. Table 2 shows the results obtained for NBS SRM 134 high speed steel alloy. Table 3 shows the results obtained for NBS SRM 62d manganese bronze alloy. All results were obtained using the same set of pure element reference spectra. Typically, percentage errors in the analyses were less than 1 percent for elements present at greater than 2 weight percent in the sample. However, an error of 3.48 percent was obtained for the analysis of chromium present at 3.60 weight percent in NBS SRM 134 (Table 2) and an error of 1.10 percent was obtained for copper present at 59.67 weight percent in NBS SRM 62D (Table 3). In general, the accuracy of the analyses deteriorated as concentrations decreased below 2 weight percent and elements present at less than 0.1 weight percent were not detected. These results compare favourably with those obtained by Desborough and Heidel⁵ who used electron beam excitation and a more complicated system consisting of several single channel analyzers to obtain quantitative analytical results.

The precision of the analytical results obtained using this technique was expressed by a calculation of the range (difference between highest and lowest) of the determined elemental weight percentages of three separate analyses of the same area on each of the three alloys. As shown in Tables 1, 2, and 3 the range was never greater than one weight percent for any of the elements determined. In general, the precision of the analyses was found to decrease as elemental concentrations increased. That is, the range of a set of analyses was larger for elements present at higher weight percent compositions. This finding was evident in all of the alloys analyzed and is due to the fact that the standard deviation of a given number of collected x-ray counts varies as the square root of the number of counts.

The analysis volume (volume from which X-rays were emitted) was calculated to be of the order of $10^{-4} \mu\text{m}^3$ using an average X-ray escape depth of $1 \mu\text{m}$ and a minimum beam diameter of $1 \times 10^{-2} \mu\text{m}$. This capability of the SEM-XES system to provide a quantitative "point" chemical analysis of such small sample volumes has many useful applications. For instance, the SEM-XES combination has been used to analyze small particulate wear debris collected from lubricating oils by filtration or ferrography. Also, a "point" analysis can provide elemental concentration profiles across a diffusion boundary which can be used to calculate the diffusion coefficient of one element into the sample matrix.

The technique used to obtain material balance in the chemical analysis provided added certainty in the analyses since the total of the determined elements in each sample was at least 97 percent. An immediate advantage of this capability is that a single element for which no reference spectrum is available can be calculated by difference. For example, if an alloy is found to contain an element from the qualitative analysis but no reference spectrum is available then a reasonable estimate of the concentration of that element can be obtained by doing a material balanced quantitative analysis and subtracting the total determined concentrations from 100 percent. This procedure can only be used to determine one additional element in each sample and the analyst must be certain that that element is present in the sample.

5. SUMMARY

A procedure was developed to obtain quantitative elemental analysis of flat polished metallic specimens using a scanning electron microscope and X-ray energy spectrometer. The technique enables the acquisition of chemical information from micro quantities of sample or from small areas of interest in the matrix of larger samples. Accurate and reproducible quantitative results were obtained on areas of the order of $10^{-6} \mu\text{m}^2$. The technique is considered a surface analysis technique because only X-rays from approximately $1 \mu\text{m}$ deep in the sample are detected. An accuracy of ± 1 percent was typical for the determination of elements present at greater than 2 weight percent. A sensitivity of approximately 0.1 weight percent was found for most elements.

ACKNOWLEDGEMENT

The author wishes to acknowledge the assistance provided by Mr. D.O. Morehouse in preparing samples and operating the scanning electron microscope.

TABLE 1

MONEL TYPE ALLOY - NBS SRM 162a

<u>Element</u>	<u>Determined Composition Weight %</u>	<u>Range Weight %</u>	<u>NBS Certified Composition Weight %</u>	<u>Error Percent</u>
Ni	64.10	0.96	63.95	0.23
Cu	30.42	0.53	30.61	0.62
Fe	2.17	0.15	2.19	0.91
Mn	1.48	0.08	1.60	7.50
Si	0.97	0.10	0.93	4.30
Al	0.45	0.08	0.50	10.00
Cr	N.D.	--	0.042	--
Co	N.D.	--	0.076	--
Ti	N.D.	--	0.005	--
Ca	N.D.	--	0.013	--
S	N.D.	--	0.007	--
C	N.D.	--	0.079	--
TOTAL	99.59			

Note: N.D. = Not Detected

TABLE 2

High Speed Steel Alloy - NBS SRM 134

<u>Element</u>	<u>Determined Composition Weight %</u>	<u>Range Weight %</u>	<u>NBS Certified Composition Weight %</u>	<u>Error Percent</u>
Fe	82.04	0.50	82.01	0.04
Cr	3.60	0.38	3.73	3.48
Mo	8.70	0.50	8.68	0.23
W	1.71	0.42	1.82	6.04
V	1.19	0.11	1.13	5.30
Mn	0.22	0.06	0.155	29.55
Si	0.29	0.10	0.323	10.22
Ni	N.D.	--	0.077	--
S	N.D.	--	0.006	--
P	N.D.	--	0.016	--
C	N.D.	--	0.810	--
<hr/>				
TOTAL	97.75			

Note: N.D. = Not Detected

TABLE 3

Manganese Bronze Alloy - NBS SRM 62d

<u>Element</u>	<u>Determined Composition Weight %</u>	<u>Range Weight %</u>	<u>NBS Certified Composition Weight %</u>	<u>Error Percent</u>
Cu	59.67	0.97	59.02	1.10
Zn	37.07	0.97	37.14	0.19
Al	1.19	0.08	1.23	3.25
Mn	0.57	0.10	0.66	13.64
Sn	0.36	0.08	0.38	5.26
Fe	0.88	0.08	0.89	1.12
Ni	0.23	0.04	0.28	17.86
Pb	N.D.	--	0.23	--
Si	N.D.	--	0.075	--
TOTAL	99.97			

Note: N.D. = Not Detected




FIG. 1: Cross-section of Electron Capturing Device

REFERENCES

1. Moseley, H.: "The High Frequency Spectra of the Elements", Philosophical Magazine, PHMAA, 26m (4), 1913.
2. Frankel, R.S. and Aithen, D.W.: Applied Spectroscopy 24, 558, 1970.
3. Beaman, D.R. and Isasi, J.A.: "Electron Beam Microanalysis", Amer. Soc. Testing Mater., Special Publication 506, 1972.
4. Beaman, D.R. and Solosky, L.F.: "Accuracy of Quantitative Electron Probe Microanalysis with Energy Dispersive Spectrometers", Anal. Chem, 44, (9), 1972.
5. Desborough, G.A. and Heidel, R.H.: "Characteristics, Performance and Analytical Capability of an Energy-Dispersive Spectrometer on an Electron Microprobe Using Low Operating Voltages", Applied Spectroscopy, 27, (6), 1972.
6. Wright, P.W.: "Procedure for Quantitative Electron Probe Microanalysis", Anal. Chem., 45, (1), 1973.
7. Duham, A.C. and Wilkinson, F.L.F.: "Accuracy, Precision and Detection Limits of Energy-Dispersive Electron-Microprobe Analysis and Silicates", Heydon and Son Limited, 1978.
8. Hurley, R.G. and Goss, R.L.: "Quantitative Energy-Dispersive X-ray Analysis Using Relative k-ratios", Heydon and Son Limited, 1978.
9. Blum, F. and Brandt, M.P.: "The Evaluation of the Use of a Scanning Electron Microscope Combined with an Energy Dispersive X-ray Analyzer for Quantitative Analysis", X-ray Spectrometry, 2, 1973.
10. Green, L.: Journ. of Phys. E. Scient. Instrum., 2, (3), 1973.
11. Wodke, Norbert F. and Schamber, Frederick, NS 885 Super ML Operation and Programme Description Version 1, Unpublished, Tracor Northern, 2551 West Beltline Highway, Middleton, Wisconsin, 1976.
12. Schamber, Frederick and Wodke, Norbert F. and McCarthy, J.M., NS 883A ZAF Operation and Programme Description Version 8A, Unpublished, Tracor Northern, 2551 West Beltline Highway, Middleton, Wisconsin, 1976.

13. Colby, J.W.: "Magic IV, A Computer Program for Quantitative Electron Microprobe Analysis", Unpublished, Bell Telephone Laboratories, Inc., Allentown, Pennsylvania.
14. Duncumb, P. and Reed, S.J.B.: "The Calculation of Stopping Power and Backscatter Effects in Electron Probe Microanalysis, Quantitative Electron Probe Microanalysis", NBS Special Publication 298, 1968.

UNCLASSIFIED

Security Classification

DOCUMENT CONTROL DATA - R & D		
(Security classification of title, body of abstract and indexing annotation must be entered when the overall document is classified)		
1. ORIGINATING ACTIVITY Defence Research Establishment Atlantic, Dockyard Laboratory, FMO Halifax, N.S. B3K 2X0		2a. DOCUMENT SECURITY CLASSIFICATION Unclassified
		2b. GROUP
3. DOCUMENT TITLE Quantitative Electron Probe Microanalysis Using a Scanning Electron Microscope and an X-ray Energy Spectrometer		
4. DESCRIPTIVE NOTES (Type of report and inclusive dates) Tech Memo		
5. AUTHOR(S) (Last name, first name, middle initial) Veinot, Dwight E.		
6. DOCUMENT DATE April 1980	7a. TOTAL NO. OF PAGES 20	7b. NO. OF REFS 14
8a. PROJECT OR GRANT NO.	8b. ORIGINATOR'S DOCUMENT NUMBER(S) DREA TECHNICAL MEMORANDUM 80/A	
8c. CONTRACT NO.	8d. OTHER DOCUMENT NO.(S) (Any other numbers that may be assigned this document)	
9. DISTRIBUTION STATEMENT		
11. SUPPLEMENTARY NOTES	12. SPONSORING ACTIVITY Defence Research Estab. Atlantic 9 Grove Street Dartmouth, N.S.	
13. ABSTRACT A procedure was developed to utilize a scanning electron microscope and X-ray energy spectrometer to obtain quantitative elemental analysis. The precision and accuracy of an X-ray intensity ratio data processing technique has been evaluated. In general, the quantitative results obtained were accurate to better than ± 1 percent of the certified elemental compositions of standard reference materials for all elements present at greater than 2 weight percent. Results were reproducible to better than 1 percent of the determined percentage compositions. Elements present at less than 0.1 weight percent composition and elements having atomic numbers less than 11 (sodium) were not detected.		

17618
74-070

UNCLASSIFIED

Security Classification

KEY WORDS

Quantitative
Electron Probe
Microanalysis
Scanning Electron Microscope

INSTRUCTIONS

1. **ORIGINATING ACTIVITY:** Enter the name and address of the organization issuing the document.
- 2a. **DOCUMENT SECURITY CLASSIFICATION:** Enter the overall security classification of the document including special warning terms whenever applicable.
- 2b. **GROUP:** Enter security reclassification group number. The three groups are defined in Appendix M of the DRS Security Regulations.
3. **DOCUMENT TITLE:** Enter the complete document title in all capital letters. Titles in all cases should be unclassified. If a sufficiently descriptive title cannot be selected without classification, show title classification with the usual one-capital-letter abbreviation in parentheses immediately following the title.
4. **DESCRIPTIVE NOTES:** Enter the category of document, e.g. technical report, technical note or technical letter. If appropriate, enter the type of document, e.g. interim, progress, summary, annual or final. Give the inclusive dates when a specific reporting period is covered.
5. **AUTHOR(S):** Enter the name(s) of author(s) as shown on or in the document. Enter last name, first name, middle initial. If military, show rank. The name of the principal author is an absolute minimum requirement.
6. **DOCUMENT DATE:** Enter the date (month, year) of Establishment approval for publication of the document.
- 7a. **TOTAL NUMBER OF PAGES:** The total page count should follow normal pagination procedures, i.e., enter the number of pages containing information.
- 7b. **NUMBER OF REFERENCES:** Enter the total number of references cited in the document.
- 8a. **PROJECT OR GRANT NUMBER:** If appropriate, enter the applicable research and development project or grant number under which the document was written.
- 8b. **CONTRACT NUMBER:** If appropriate, enter the applicable number under which the document was written.
- 9a. **ORIGINATOR'S DOCUMENT NUMBER(S):** Enter the official document number by which the document will be identified and controlled by the originating activity. This number must be unique to this document.
- 9b. **OTHER DOCUMENT NUMBER(S):** If the document has been assigned any other document numbers (either by the originator or by the sponsor), also enter this number(s).
10. **DISTRIBUTION STATEMENT:** Enter any limitations on further dissemination of the document, other than those imposed by security classification, using standard statements such as:
 - (1) "Qualified requesters may obtain copies of this document from their defence documentation center."
 - (2) "Announcement and dissemination of this document is not authorized without prior approval from originating activity."
11. **SUPPLEMENTARY NOTES:** Use for additional explanatory notes.
12. **SPONSORING ACTIVITY:** Enter the name of the departmental project office or laboratory sponsoring the research and development. Include address.
13. **ABSTRACT:** Enter an abstract giving a brief and factual summary of the document, even though it may also appear elsewhere in the body of the document itself. It is highly desirable that the abstract of classified documents be unclassified. Each paragraph of the abstract shall end with an indication of the security classification of the information in the paragraph (unless the document itself is unclassified) represented as (TS), (S), (C), (R), or (U).

The length of the abstract should be limited to 20 single-spaced standard typewritten lines; 7 1/4 inches long.
14. **KEY WORDS:** Key words are technically meaningful terms or short phrases that characterize a document and could be helpful in cataloging the document. Key words should be selected so that no security classification is required. Identifiers, such as equipment model designation, trade name, military project code name, geographic location, may be used as key words but will be followed by an indication of technical content.